



Waterlox Coatings Corporation
9808 Meech Avenue • Cleveland, OH 44105
Phone: 216.641.4877 • Fax: 216.641.7213
www.waterlox.com

Waterlox Original Marine Finish (Exterior Grade)



Description

Waterlox Original Marine Finish is a clear, high gloss finish coat, which penetrates wood enabling it to resist moisture, the harmful UV rays of the sun, salt and fresh water exposure, and heat and cold.

Uses

Waterlox Original Marine Finish is recommended for all exterior wood surfaces as a finish coat, such as marine furniture, paneling, all boat woodwork, exterior furniture, doors, railings, fences and decks. When used in combination with Waterlox Original Sealer/Finish, Waterlox Original Marine Finish renders a hand-rubbed appearance in a high gloss sheen.

Preparation of Surfaces

Apply to a small test area and allow to dry prior to applying to the entire surface. Final color effect is always influenced by the grain, texture, porosity, species of wood, number of coats and by method of application.

Strip previously finished surfaces to bare wood. Where not possible to strip all wood, Waterlox Original Sealer/Finish can be used as a primer/tie-coat. If the previous finish is a urethane or unknown, the finish must be abraded before application. Sand the surface well and wipe clean with a tack cloth or cloth dampened with paint thinner.

Application

Application methods include lambswool, brush, roller, or cloth.

Sanding between coats is not necessary for adhesion purposes, for aesthetic reasons, you can perform a light sanding with fine sandpaper, steel wool (0000) or buff with a 3M® white pad.

Staining with Waterlox

Stain can be added to your first coat of Waterlox Original Sealer/Finish. You can add up to 1 quart of oil-based stain to 1 gallon of Waterlox Original Sealer/Finish. We recommend you use an old-fashioned oil-based stain (without additives such as urethane).

Coverage

One gallon of Waterlox Original Marine Finish covers 400 square feet per gallon per coat. Thinning is not necessary.

Recoatability

Once the gloss level of the film begins to fade it is time to re-coat the surface. Sanding down to bare wood is not necessary. Simply clean the surface and re-coat with more Waterlox Original Marine Finish and allow to dry.

Dry Time

After each coat has been applied, allow to air dry for 6-24 hours, or until tack-free. Dry time depends on temperature, ventilation and humidity. For best results apply when temperatures are over 60°F, and when humidity is relatively low. Dry time will increase due to low temperatures or high humidity.

Clean Up/Storage

Use mineral spirits or turpentine to clean tools, equipment, applicators and spills. Then wash with warm soapy water.

Transfer unused Waterlox Original Marine Finish to smaller tightly sealed jars or raise the level in the original container by adding clean marbles or stones. This is to prevent the potential jelling of contents due to air exposure within the can.

Cautions

Do not use over wax. To avoid spontaneous combustion during temporary storage, soak soiled rags and waste immediately after use in a water-filled, closed metal container. For MSDS information, visit our website at www.waterlox.com.

DANGER! CONTAINS MINERAL SPIRITS. COMBUSTIBLE LIQUID AND VAPOR. HARMFUL OR FATAL IF SWALLOWED. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN.

**Waterlox Tung Oil Penetrates • No Sanding Necessary for Adhesion • Great for use with Exotics •
Protects against moisture, heat/cold, household chemicals • Very easy to apply, maintain & re-coat
Visit us on the web at www.waterlox.com for more information**