

Waterlox Product Specifications

Product	Product Number	Sheen	Product Use	Wt Solids +/- .1%	Wt/Gal	Hrs. Dry to Touch ⁴	Hrs. Dry Hard ⁴	Hrs. Dry Re-Coat ⁴	VOC Gr/L	Coverage ³ Per Gallon
Waterlox Original Sealer/Finish	TB5284	Medium	Sealer Finish	26.3	6.95	2 - 4	12+	8 ¹	614	500 Sq. Ft.
Citrus Scent Original Sealer/Finish	TB6031	Medium	Sealer Finish	26.9	6.78	2 - 4	12+	8 ¹	595	500 Sq. Ft.
Waterlox Original 350 VOC Sealer/Finish	TB6040	Medium	Sealer Finish	19.18	9.68	2 - 4	12+	8 ¹	345	500 Sq. Ft.
Waterlox Original Satin Finish	TB6022	Satin	Finish	28.1	6.97	2 - 4	12+	8 ¹	600	500 Sq. Ft.
Citrus Scent Original Satin Finish	TB6033	Satin	Finish	27.3	6.85	2 - 4	12+	8 ¹	585	500 Sq. Ft.
Waterlox Original 450 VOC Satin Finish	TB6045	Satin	Finish	33.99	8.25	2 - 4	12+	8 ¹	445	500 Sq. Ft.
Waterlox Original 350 VOC Satin Finish	TB6035	Satin	Finish	30.70	9.10	2 - 4	12+	8 ¹	345	500 Sq. Ft.
Waterlox Original High Gloss Finish	TB3182	High Gloss	Finish	39.2	7.18	4 - 6	12+	8 ¹	523	500 Sq. Ft.
Waterlox Original Marine Finish	TB3940	High Gloss	Finish	49.6	7.44	6 - 8	12+	12+	450	500 Sq. Ft.
Waterlox Original Marine Sealer	TB3809	Medium	Exterior Primer	26.3	6.95	2 - 4	12+	8 ¹	614	500 Sq. Ft.
Urethane Satin XL-89	TB5930	Satin	Finish	43.1	7.35	2 - 4	8	6 ¹	501	450 Sq. Ft.
Urethane Gloss XL-88	TB4252	Gloss	Finish	39.9	7.22	2 - 4	8	6 ¹	520	450 Sq. Ft.
Urethane Semi-Gloss XL-90	TB5824	Semi-Gloss	Finish	40.8	7.25	2 - 4	8	6 ¹	515	450 Sq. Ft.
Cement Stain 2000	²	Satin	Finish	56.0	9.79	4	12+	Overnight	515	200 Sq. Ft.

1 Overnight Recommended 2 Specifications are based on CS2000 White. See Color Card for other colors

3 Average 4 Based on 70°F; <50% relative humidity; and adequate ventilation